

PATENT ABSTRACTS OF JAPAN

(11)Publication number : **62-141565**

(43)Date of publication of application : **25.06.1987**

(51)Int.Cl.

G03G 5/10

(21)Application number : **60-281200**

(71)Applicant : **FUJI XEROX CO LTD**

(22)Date of filing : **16.12.1985**

(72)Inventor : **KITO SHIRO
TAKEGAWA ICHIRO
SAKAGUCHI YASUO
NAKAMURA KAZUYUKI
YAMAZAKI HIDEKO**

(54) **ELECTROPHOTOGRAPHIC SENSITIVE BODY**

(57)Abstract:

PURPOSE: To enhance electric conductivity by using a conductive substrate made of a resin containing reduced potassium titanate whiskers.

CONSTITUTION: The electrophotographic sensitive body is obtained by dispersing the reduced potassium titanate whiskers as a conductive powder into the plastic resin, forming it on a cylinder, and laminating a photosensitive layer on this conductive substrate. These whiskers are single crystal fibers, each represented by $K_2O \cdot nTiO_2$, usually having resistivity as high as $10^{15} \Omega \cdot cm$, therefore, they are reduced to lessen the oxygen content to less than the stoichiometric quantity into a oxygen deficient state in order to lower the resistivity. The reduced potassium titanate whiskers are composed of dark gray acicular crystals, and they have a resistivity of $10^{-2} - 10^5 \Omega \cdot cm$, an average fiber length of $8 \times 10^2 \mu m$, an average fiber diameter of $0.2 - 0.7 \mu m$, and a specific gravity of 3.1 - 3.3.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2000 Japan Patent Office